

# Trimite J125

## Methacrylate Lacquer

<b>Description</b>	A clear, water-white lacquer for non-ferrous alloys.			
<b>Finish</b>	Neutral.			
<b>Features</b>	<ul style="list-style-type: none"> <li>• Can be applied as a thin coat on polished brass, copper, silver and many alloys.</li> <li>• Prevents attack and tarnishing by atmospheric oxygen and industrial pollutants.</li> <li>• The clarity and excellent optical properties of the lacquer ensures that the original appearance of the substrate is preserved.</li> </ul>			
<b>Complies With</b>	Please consult Trimite.			
<b>Product Code</b>	<b>J125- .</b>			
<b>Volume Solids</b>	Please consult Trimite.			
<b>VOC's</b>	Please consult Trimite.			
<b>Colour Range</b>	Clear lacquer.			
<b>Film Thickness &amp; Coverage</b>	<b>Typical:</b>	<b><u>Dry</u></b> 20 µm	<b><u>Wet*</u></b> 50 µm	<b><u>Approx. Coverage*</u></b> 6 - 7 m <sup>2</sup> /l
	<p>* The above wet film thicknesses and approximate coverage rates may vary with a variety of factors. Wet film thicknesses are approximate.</p> <p>Actual coverage varies considerably with factors including surface porosity, roughness, application methods and conditions.</p>			
<b>Drying &amp; Overcoating Times at Typical DFT</b>		<b><u>10°C</u></b>	<b><u>20°C</u></b>	<b><u>30°C</u></b>
	Surface Dry:	1 h	30 min	15 min
	Hard Dry:	12 h	6 h	3 h
	Overcoat Min:		see below*	
	<p>* not normally overcoated, please consult Trimite for advice.</p> <p>Drying and overcoating times can be greatly affected by method and conditions of application such as thickness applied, temperature, ventilation etc. Data above are given as a guide.</p>			

**TECHNICAL DATA SHEET****Trimite J125**  
**Methacrylate Lacquer**

<b>Surface Preparation</b>	<ul style="list-style-type: none"><li>The substrate must be thoroughly clean, dry and free from corrosion and contaminants.</li></ul>
<b>Mixing</b>	Thoroughly stir the coating before use. A wide-bladed stirrer is essential for adequate mixing if only hand stirring. Stir occasionally during use to maintain an homogenous mix.
<b>Mix Ratio</b>	Not applicable – single pack product.
<b>Application Conditions</b>	Throughout the application and the drying/curing time of coatings: (a) good ventilation is required; (b) do not apply when damp weather conditions are likely; (c) the substrate temperature should be at least 3°C above the Dew Point; and (d) the RH (Relative Humidity) should be below 85%. It is advisable not to apply the product when the ambient temperature falls below 5°C. The paint temperature at the time of application should ideally be 15° - 20°C.
<b>Application Details</b>	<ul style="list-style-type: none"><li>Designed for application by conventional spray, supplied ready for use.</li><li>A small amount of CT80 Thinner may be added to improve flow and general appearance.</li></ul>
<b>Thinner/Cleaner</b>	J103 Gun Cleaner (as Cleaner).
<b>SG</b>	0.916 ± 0.1 kg/l.
<b>Flash Point</b>	Below 23°C – LOW FLASH MATERIAL.
<b>Shelf Life</b>	Min. 1 year from date of delivery when correctly stored in unopened containers.
<b>Storage</b>	The product should be stored in cool, dry, frost-free conditions, in sealed containers. Most paint materials will apply optimally when at 15° - 20°C.
<b>Health &amp; Safety</b>	Refer to the product's Safety Data Sheet and safety advice on the product label before use.
<b>Date of Issue</b>	June 2024.

Information provided in this leaflet is given in good faith but without warranty or assumed liability, as the conditions of application and use are beyond our control. Data are accurate to the best of our knowledge at the time of issue but may be revised in the light of new knowledge and the user should check that data are current before use. The user must satisfy themselves about the product's suitability for their own purpose and refer to the Safety Data Sheet for this product before use. For industrial or professional use only unless specifically stated otherwise.